



Stainless Steel International Comparison Specifications

W-Nr	Din	AISI	UNS	SS	AFNOR	BS
1.4005	X 12 CrS 13	416	S 41600	2380	Z 11 CF 13	416S21
1.4006	X 12 Cr 13	410	S 41000	2302	Z 10 C 13	410S21
1.4016	X 6 Cr 17	430	S 43000	2320	Z 8 C17	430S17
1.4021	X 20 Cr 13	420	S 42000	2303	Z 20 C13	420S37
1.4034	X 46 Cr 13			2304	Z 44 C14	420S45
1.4057	X 17 CrNi 16 2	431	S 43100	2321	Z 15 CN 16.02	431S29
1.4104	X 14 CrMos 17	430F	S 43020	2383	Z 13 CF 17	416S21
1.4112	X 90 CrMos 18	440 B	S 44003			
1.4122	X 39 CrMo 17 1					
1.4301	X 5 CrNi 18 10	304	S 30400	2332	Z 6 CN 18.09	304S15
1.4305	X 8 CrNiS 18 9	303	S 30300	2346	Z 8 CNF 18.09	303S31
1.4306	X 2 CrNi 19 11	304L	S 30403	2352	Z 2 CN 18.09	304S11
1.4310	X 10 CrNi 18 8	301	S 30100	2331	Z 12 CN 18.09	301S22
1.4313	X 3 CrNiMo 13 4			2384	Z 4 CND 1304	425C11
1.4401	X 5 CrNiMo 17 12 2	316	S 31600	2347	Z 7 CND 17.12.02	316S31
1.4404	X 2 CrNiMo 17 12 2	316L	S 31603	2348	Z 3 CND 18.12.02	316S11
1.4435	X 2 CrNiMo 18 14 3	316L	S 31603	2353	Z 3 CND 18.14.03	316S11
1.4436	X 3 CrNiMo 17 13 3	316	S 31600	2343	Z 7 CND 18.12.03	316S31
1.4438	X 2 CrNiMo 18 15 4	317L	S 31703	2367	Z3 CND 19.15.04	317S12
1.4439	X 2 CrNiMoN 17 13 5	317 LNM				
1.4449	X 5 CrNiMo 17 13	317	S 31700			317S16
1.4460	X 3 CrNiMoN 27 52	329	S 32900	2324	Z 5 CND 27.05 AZ	
1.4462	X 2 CrNiMoN 22 53		S 31803	2377	Z 3 CND 22.05 AZ	
1.4539	X 1 NiCrMoCu 25 20 5		N 08904	2562	Z 1 NCDU 25.20	
1.4541	X 6 CrNiTi 18 10	321	S 32100	2337	Z 6 CNT 18.10	321S31
1.4542	X 5 CrNiCuNb 16 4	630			Z 7 CNU 17.04	
1.4550	X 6 CrNiNb 18 10	347	S 34700	2338	Z 6 CNNb 18.10	347S31
1.4571	X 6 CrNiMoTi 17 12 2	316Ti	S31635	2350	Z 6 CNDT 17.12	320S31
1.4713	X 10 CrAl 7				Z 8 CA 7	
1.4724	X 10 CrAl 13				Z 13 C 13	
1.4742	X 10 CrAl 18				Z 12 CAS 18	
1.4749	X 18 CrN 28	446-1	S 44600	2322		
1.4762	X 10 CrAl 24	446	(S 44600)	2322	Z 12 CAS 24	
1.4821	X 20 CrNiSi 25 4				Z 20 CNS 25.04	
1.4828	X 15 CrNiSi 20 12	309	(S 30900)		Z 17 CNS 20.12	309S29
1.4841	X 15 CrNiSi 25 20	314	S 31400		Z 15 CNS 25.20	314S25
1.4845	X 12 CrNi 25 21	310S	S 31008	2361	Z 12 CN 25 20	310S24
1.4864	X 12 NiCrSi 36 16	330	N 08330		Z 20 CNS 35.16	3076 NA 17
1.4876	X 10 NiCrAlTi 32 20	B 163			Z8 NC 33.21	3076 NA 15 H
1.4878	X 12 CrNiTi 18 9	321	S 32100	2337	Z 6 CNT 18.10	321S51
2.4068	LC Ni 99	B 160				
2.4360	Ni Cu 30 Fe	B 164				3076 NA 13
2.4375	Ni Cu 30 Al					3076 NA 18
2.4610	Ni Mo 16 Cr 16 Ti					3076 NA 45
2.4816	Ni Cr 15 Fe	B 166				3076 NA 14
	Ni Cr 21 Mo					3076 NA 43